

AMENDMENT NO. 2 SEPTEMBER 2017
TO
IS 14887 : 2014 TEXTILES — HIGH DENSITY
POLYETHYLENE (HDPE)/ POLYPROPYLENE (PP)
WOVEN SACKS FOR PACKAGING OF
50kg FOOD GRAINS — SPECIFICATION

(First Revision)

[Page 2, Table 1, Sl No. (i)] — Delete.

[Page 2, Table 1, Sl No. (viii) and (ix)] — Substitute the following for the existing:

Sl No.	Characteristic(s)	Requirement(s)	Tolerance	Method of Test, Ref to
(1)	(2)	(3)	(4)	(5)
viii)	Elongation at break of fabric, (revelled strip method), percent :			IS 1969 (Part 1)
	a) Lengthwise	15 to 25	—	
	b) Widthwise	15 to 25	—	
ix)	Breaking strength of fabric after exposure to UV radiation and weathering, <i>Min</i>	50 percent of original strength	—	Annex C

(Page 5, clause **D-1**, lines 4 and 5) — Substitute ‘590°C’ for ‘550°C’.

(Page 5, clause **D-2.5**, line 2) — Substitute ‘590°C’ for ‘550°C’.

(Page 6, clause **D-4.1**, line 1) — Substitute ‘590°C’ for ‘550°C’.

(Page 6, clause **D-4.5**, line 2) — Substitute ‘590°C’ for ‘550°C’.